Amendments to the Specification:

Please replace the paragraph beginning at page 23, line 2, with the following amended paragraph:

In ar. embodiment, the invention is a single ply paper product with comprising a paper substrate having a first surface and a second surface and comprising a web of fibers sufficiently refined to have a Canadian Standard Freeness value of greater than about 100 cm³ according to TAPPI standard test T 227, and having a weight of between about 20 lbs./3,000 ft.² and about 45 lbs./3,000 ft.²; and a fluorochemical in an amount of at least 800 parts per million. In another embodiment, the invention is a method for processing a single ply paper product including comprising the steps of folding a single ply paper product includes at least one of folding, creasing, applying adhesive, applying a susceptor patch, and heat scaling. In another embodiment, the invention is an article with comprising a single ply paper product and a charge of oil and popcorn.